Cathodic protection of marine structures

J. S. BALFOUR

Mr R. A. Hine, Alcan Research and Development Ltd

This Technical Note provides an interesting summary on the cathodic protection of marine structures. However, we feel that the comment 'It is understood that aluminium anodes are beginning to be favoured for economic reasons . . .' is a considerable understatement of the present position.

The development of special aluminium alloy anodes having outputs in excess of 1000 A h/lb has resulted in their widespread use for cathodic protection of marine structures. Several types of high-efficiency anode are produced by manufacturers in this country and abroad; they all show open-circuit potentials in the range -1.05 to -1.25 V (versus silver/silver chloride electrode) and hence provide adequate protective potential but with a minimum risk of cathodic paint stripping on painted structures. They have been used for at least six years for the protection of ships' hulls and ballast tanks and are finding increasing use for the protection of other marine structures. Successful applications range from the protection of small items such as anchors and mooring chains to the employment of giant anodes for protecting offshore drilling rigs. A particularly interesting example from the standpoint of this Technical Note is the use of aluminium anodes (Alcan 420 alloy) for the protection of the interior compartments of the Haringvliet sluice gates, a major installation in the Rhine Delta project.

Mr Balfour

The conclusions outlined in this Technical Note were derived from the answers given to the questionnaire on cathodic protection issued by the Institution. In fact thirty marine structures were reported and in no case were aluminium anodes used. Accordingly in the Note only a brief reference could be made to their use.