Discussion.

The Chairman. The CHAIRMAN moved a vote of thanks to the Authors for their Papers.

Mr. Greaves. Mr. R. H. GREAVES referred to work on the deformation of notched-bar test-pieces, which he had carried out with the assistance

Figs. 1.

STRAIN HARDENING OF $\frac{1}{4}$ MM. RADIUS V-NOTCH TEST-PIECES, BENT AND BROKEN IN A CHARPY MACHINE.

of Miss M. Fell, B.Sc., and Miss L. Grieve, B.Sc. In this connection the distribution of strain hardening had been examined by the Brinell method, using a ball of 1 millimetre diameter. Many

impressions could thus be made on a prepared surface or section of the test-piece. On the evidence of the hardness tests it was possible to represent the general distribution of strain hardening. *Figs. 1* and *2* showed the distribution of hardening on nickel-chromium steel test-pieces with notches of 0.25 millimetre and 1 millimetre radius, partially and completely broken. The original hardness was under 210 and the successive lines *a* to *e* represented approximate increments of 10 Brinell units from 210 upwards. At the beginning of bending the strain hardening occurred in an annular zone joining the notch to the point of contact of the knife edge, the central part of the

Figs. 2.

STRAIN HARDENING OF 1 MM. RADIUS NOTCH TEST-PIECES, BENT AND BROKEN IN A CHARPY MACHINE.

zone remaining unhardened. On further bending the lines of equal hardness showed an inflection near the middle of the test-piece, indicating less strain hardening than on either side. The region affected by strain hardening was more extended with the rounded notch: in brittle material it shrank up to the immediate vicinity of the notch and could only be recognized by Brinell tests near the point of impact of the pendulum. Deformation was also studied by the surface cracking of a brittle skin. Heating polished test-pieces in ammonia at 600°–650° C. for 2 hours resulted in the formation of a thin nitrified layer containing nitride of iron. Using oil-hardened and tempered nickel-chromium steel, the impact figure

Mr. Greaves. could be controlled by the rate of cooling from this temperature. The nitrified layer was extremely hard and brittle, and when the test-piece was subsequently broken, yielding of the steel was not accompanied by corresponding yielding of the skin. Hence regular systems of minute cracks were formed on the surface, leaving a permanent indication of the deformation which had occurred in each region. The regions of tension showed long continuous cracks, which were presumably at every point at right angles to the direction of maximum extension. Regions of compression showed more confused cracks and corrugations. [Lantern slides of photographs, taken by oblique illumination, were exhibited by the speaker.] In very brittle material the cracks were confined to a narrow strip in close proximity to the fracture. The region affected was larger, the larger the radius of the notch. The tougher specimens showed a more pronounced lateral spread of the region in tension, while the region in compression occupied a greater depth in the test-piece. All specimens broken in the Charpy machine, or slowly between supports, showed approximately symmetrical systems of cracks. Those broken in the Izod machine were, however, not symmetrical, the region of tension extending farther to the side of the notch held by the vice than in the direction of the knife edge. This unsymmetrical distribution of deformation was supported by hardness measurements. These results served to illustrate the complex nature of the deformation which occurred in notched-bar impact test-pieces, and raised the question how far geometrical similarity of the regions of deformation could be obtained by varying the external dimensions of the test-piece.

Dr. Hatfield. Dr. W. H. HATFIELD congratulated Dr. Stanton and Mr. Batson upon their extremely constructive and valuable Paper. Notched-bar testing had become very fashionable of late, and many people had been using it, but they had arrived at different conclusions as to its real utility as an indication of the behaviour of material under working conditions. For instance, railway tires and other engineering parts which under the shock test gave extremely low values, could not be considered intrinsically brittle; and he might mention also an anomalous fact within his experience. During the war the Aeronautical Inspection Department were very much concerned with airplane crank-shafts, and a specification was drawn up which required 35 to 45 lbs. Izod impact value. When the matter was discussed he suggested that it would be instructive to receive back from France crank-shafts from engines which had given good service. That was done, and it was instructive to find when those shafts were examined that some of the Izod values were very good,

but some were very low. On the other hand, some of his friends— Dr. Hatfield. and some of the Authors of these Papers—were very insistent on the necessity for high notched-bar values if the part was to be severely stressed. He felt that both those who accepted the utility of Izod tests and Charpy tests as indications of good service, and those who took the opposite view, were equally vindicated by the Paper by Dr. Stanton and Mr. Batson. It should be borne in mind that the standard notched-bar tests were arbitrary tests on bars of sizes arbitrarily chosen, and with arbitrarily chosen velocity; under those conditions certain results were obtained from particular steels. At the top of p. 79 Dr. Stanton and Mr. Batson said:— “For the same two materials, when in the form of the British Standard specimen, the mild steel absorbed three times as much energy as the hard steel, whereas when the specimen was 63×63 millimetres, and the notch had the same root radius, the energy absorbed by the mild steel was 20 per cent. *less* than that of the hard steel.” And on p. 81, speaking of variable velocity:—“Thus there is a group of materials, including all the irons and some of the low-carbon steels, in which there is a very marked reduction of energy absorbed with increase of speed. On the other hand, the high-carbon steels do not appear to be appreciably affected, and in the case of the nickel-chrome steel there is a definite rise in the energy absorbed as the speed increases.” That experimental evidence showed pretty clearly that, interesting as were the data brought out by a notched-bar test made under certain arbitrary conditions, there was no direct relationship between those data and the performance which might be expected from the part in service. He agreed that the time would likely arrive when, as a result of further experimental work on similar lines, it would be possible to draw direct analogies from such laboratory forms of test to the service conditions. He agreed with the Authors also that the tests could not, in the light of present knowledge, be regarded as a means of determining the relative toughness of materials in their normal condition. At p. 82 the Authors said that “any algebraic expression for the work of fracture cannot be expressed as a function of the final deformation of the material only, but will probably contain a term depending on the time which has elapsed between the first contact of the hammer and the final fracture of the specimen.” If the Authors were able finally to establish that deduction by more experimental evidence, both of the kind which they were preparing and of an auxiliary kind, a fundamental step would have been taken in the progress of knowledge of the subject; and the results of the Authors’ work would be looked forward to with great interest.

Dr. Hatfield. Messrs. Greaves and Moore expressed the view that the number of cases investigated by them in which material had failed in service by cracking or fracture of some kind, and had been found to give poor results in the notched-bar test, was much too large for the association to be accidental. That view would prove interesting in the light of the evidence brought forward by Dr. Stanton. In his own research laboratories he employed seven or eight different forms of mechanical test, including ordinary tensile and torsion tests, and no instance had occurred within his experience in which the failure of a part in service had been explained by low values under the notched-bar test. That did not say that the notched-bar test was to be thrown on one side; he would be the last to say that, for he knew that extremely interesting data were disclosed by that test; but the interpretation of those data, in his opinion, was impossible with the experimental evidence at present available.

Mr. Green. Mr. VICTOR E. GREEN entirely disagreed with Dr. Hatfield's destructive criticism. Messrs. Stanton and Batson's Paper was inclined to be constructive on the subject. There did not seem to be any mention in the Paper of the time of notching, and he assumed that the heat-treated material was notched and drilled before treatment. That was, perhaps, a point on which it was desirable to be quite clear. He would like further information on the method of making the notches—whether by milling-cutters or shaping-tools. As to the time effect during the case-hardening tests, recently, on breaking the bars to obtain fracture, he had made some tests using the Izod machine as a standard to give a definite striking velocity on breaking the case-hardened specimen. He had found that a case-hardened specimen broken at a certain velocity had a very different type of fracture from that obtained with a different velocity. It seemed to him that a fibrous fracture could be obtained in steel for case-hardening purposes by bending a bar slowly, whereas if the bar were bent quickly a crystalline fracture was obtained. The method of obtaining the different velocities was not very clear from Plate 1. It seemed to him that, with the arrangement shown, only one or two velocities could be obtained. He thought the most important feature of the Paper was that a real attempt had been made to get at a design factor for impact strength. Speaking as an engineer and not as a metallurgist, he thought that was the important point. If engineers could use the impact test—which he confidently believed they would do in time—so as to introduce a design factor, such as could be done for tensile or torsional strength, many failures would be avoided. No mention was made in the Paper of the round type of impact test-piece, adopted towards the end of the war by the

Aeronautical Inspection Department. He would like to know Mr. Green, whether that had proved quite satisfactory in practice.

Mr. J. C. W. HUMFREY considered that the Papers gave valuable Mr. Humfrey. information with regard to the notched-bar test; but in view of the numerous and complicated factors which came into that test, it was surprising that the results obtained were so consistent. Some time ago Dr. Stanton and Mr. Bairstow, and subsequently Mr. Philpot, carried out tests of the slow bending of notched bars, and plotted the stress-strain curves obtained. He himself had recently carried out a large number of slow notched-bar tests on various materials, using a machine in which the test could be carried out very quickly, and with which one could get an autographic diagram of the relation between bending angle and bending moment. He had made tests with various types and depths of notch. The diagrams obtained enabled materials to be divided into two fairly definite classes, namely: (1) tough—those in which the final crack spread slowly, requiring external energy for its propagation, and (2) brittle—those in which the crack spread suddenly and violently, no external energy being required. This difference appeared to be the essential feature brought out by notched-bar tests, but in tests in which total energy alone was recorded it might be lost sight of, owing to a large portion of the energy being absorbed in deformation before the crack started. This was especially the case when using notches with a large root radius, and therefore the sharper the notch, the better was the essential feature of the test brought out. To form as sharp a notch as possible he had tried, instead of machining to the bottom of the notch, to machine down nearly to the depth required, and finish by pressing in a hard steel die with a sharp edge. That notch could be reproduced very consistently, it could be made absolutely sharp, and a possible objection to it which might be raised, namely, that the material was deformed when first tested, was not serious, because the deformation occurred more at the sides than at the angle of the notch. With regard to the effect of the size of the test-piece, he had plotted some of Dr. Stanton's results, using logarithmic co-ordinates, and had found that practically all the curves in *Fig. 5* (p. 76) became straight lines, showing that the energy expended was proportional to some power of the linear dimensions of the test-piece, which power varied according to both the materials and the form of the notch. For instance, for the O.S. steel, with the 45° notch, it was 2.17; for other metals it was different; and it differed for the Charpy and other notches. Under those conditions he did not think it could be said that there was a limiting value to the energy expended

Mr. Humfrey. with the size of the test-piece, because it was a parabolic law. He agreed with Mr. Moore that the total energy should be taken, and not the total per cubic centimetre. The difference in the velocity effects shown by Dr. Stanton and Mr. Batson for high-carbon and mild steels was very interesting; but it would be still more interesting to know whether the difference was due to the amount of energy absorbed in deformation, or whether it was due to that required for the propagation of the crack when once started.

Mr. Saniter. Mr. E. H. SANITER thought the question of notched-bar testing was very far from settled. Messrs. Greaves and Moore said (p. 102): "On the other hand, examples of steel of similar tenacity, differing widely in energy absorbed in the notched-bar test, are common, the difference usually being due to differences in composition or heat-treatment." That generalized statement might be justified to a certain extent in speaking of alloy steels. It was important, he thought, in discussing notched-bar tests, to discriminate between steel alloys and carbon steels heat-treated in the laboratory or in the works, or in the untreated condition. His experience was that impact tests on alloy steels showed fair regularity of result under careful treatment. With carbon steels regularity could not be obtained either in laboratory or works treatment. Recently Dr. Baker had made notched-bar tests on a steel of about 45 tons per square inch tensile strength, and on two consecutive notches he had found differences ranging from 12 foot-lbs. to 90 foot-lbs. on a carefully treated specimen. A test which gave results like that on carbon steels, carefully heat-treated under laboratory conditions, could not be applied to works practice until a great deal more investigation had been made. Messrs. Greaves and Moore said (p. 102): "In accordance with these considerations the single-blow impact test on notched bars is regarded as a test of ductility under localized stress. This is entirely in agreement with conclusions drawn from the behaviour in service of material giving good and bad results in the test." If that meant that material in use did deform before failing, he entirely disagreed. The great majority of the breakages in practice occurred without any deformation.

He joined with Dr. Hatfield in expressing his admiration for the large amount of work Dr. Stanton and Mr. Batson had done, and for the very able way in which it had been set out. Their Paper had brought home to him several points in connection with the impact test which he had not recognized before. Dr. Hatfield had already referred to one point he had noted, namely, the influence, on the result of a notched-bar test, of the size of the test-bar. Another point which specially interested him was that on p. 84 relating to the width of the specimens. It brought out, as the

Authors pointed out, the marked effect of deformation on the test either before or during fracture, and by widening the test-piece the deformation was very materially reduced. It had occurred to him that perhaps the only way to make any advance in regard to the notched-bar test—because the Papers did not throw much more light on the value or meaning of the test—would be to try to eliminate some of the factors which interfered with direct reading of the test. Dr. Stanton had rightly laid great stress on the deformation, and it had occurred to Mr. Saniter that a test-piece could be made which would practically eliminate deformation of the kind that interfered with the test. He had in mind a test-piece notched on three sides instead of one, and struck on the unnotched side. In his opinion that would, without increasing the width of the specimen, largely eliminate the deformation which interfered with the test, and might lead also to a modification of the effect of the speed of impact.¹

¹ The following tests were made by Dr. Baker at my suggestion comparing test-pieces notched on three sides in the same plane with the ordinary test-pieces notched on one side.

Analysis of steel: C, 0·06; Si trace; S, 0·026; P, 0·015; Mn, 0·34. Test-pieces cut from a 3-inch square billet.

	Notched on one side.		Notched on three sides.	
	Small Charpy.	120 ft.-lb. Izod.	Small Charpy.	120 ft.-lb. Izod.
	ft.-lbs.	ft.-lbs.	ft.-lbs.	ft.-lbs.
As rolled	58 ¹	74 ¹	19·5	26·0
Water quenched from 1,000° C. . . . }	153 ¹	92 ¹	108	79 ¹

¹ All these pieces were incompletely broken.

All notches were of Standard Air Board pattern, and the cross section actually broken was the same in all cases. To attain this object the bars notched on three sides were made 14 millimetres wide.

An examination of these test-pieces notched on three sides shows that distortion has been practically eliminated, even on this very tough material.

The figures show that the speed effect, which is probably only another phase of distortion, is largely, if not entirely, eliminated.

They also show the unsuitability of the Izod machine for testing very tough material.

The elimination of distortion with the test-pieces notched on three sides points out the desirability of reinvestigation of the results obtained from different sized test-pieces under these new conditions.—E. H. S.

Sir Robert
Hadfield.

SIR ROBERT HADFIELD remarked that in view of some of the statements in the other Papers, and of remarks already made, interesting as these were, it seemed to him that the full value of shock-tests, whether from the scientific or the practical point of view was still not altogether realized. He wished, therefore, to add the following suggestions, based upon lengthy experience of the idiosyncrasies of ordinary and special steels, gained since he had the honour of reading his first metallurgical Paper,¹ on "Manganese Steel," before The Institution in February, 1888. He emphasized this the more because the remarks he was going to make applied to constructive material of all kinds, and were therefore of particular interest to this Institution. The statement might appear a strong one when he said that, in his opinion, when the qualities of a particular steel were once known—tensile strength, elastic limit, elongation and reduction of area—and given satisfactory (a) composition; (b) resistance to shock—the test to be of the high-velocity type—and (c) hardness (Brinell ball test); then he would be prepared to accept and use such steel products, as were required in constructive engineering work, upon the results of these two tests alone. For example, in the case of crank-shafts such as were used for motor-cars, if the average qualities of the material were known from tensile tests, he would then be quite satisfied to select, and feel safe in making use of, a motor-car in which the particular crank-axle employed had been subjected to shock and Brinell tests with satisfactory results. He would be confident that all could afterwards be relied upon to go well. He proposed to throw on the screen illustrations of one or two products, of which quite considerable numbers were used during the war, and which were subjected, both in proof and in actual warfare, to intensely-high shock tests—namely, the impact of armour-piercing and high-explosive projectiles. The first section of the first slide represented a gun-shield of unforged material—that was, cast only and properly heat treated. The second was a cast ammunition-tube, taking the place of the more expensive forged product. The third was a conning-tower, weighing about 20 tons, as used for the monitors on which were placed the gigantic 18-inch guns. It would be seen that the first two had been subjected to very severe gun-fire; and he would emphasize the fact that these products were passed into service with the certainty that they would resist gun-fire, solely on the shock test and ball hardness number. He did not see how stronger proof of confidence in shock tests could be given. He wished here to pay a tribute of thanks to the late

¹ Minutes of Proceedings Inst. C.E., vol. xciii, p. 1.

Professor Floris Osmond, France's greatest metallurgist, who at an early stage realized the great value of, and first drew his attention to, the valuable pioneer work of Mr. Charles Frémont, the real originator of scientific and accurate shock tests. He would also refer to the excellent work on shock testing in its early days by Captain H. Riall Sankey, now President of the Institution of Mechanical Engineers; Sir Archibald Denny, Chairman of the British Engineering Standards Association; and the Notch-Bar Testing Committee of that Association presided over by Dr. Unwin. By scientific and accurate shock tests, he meant breaking the test-bar with a falling weight at the comparatively high velocity of about 29 feet per second, and providing a proper device for measuring the residual energy of the tup after the specimen had been broken. The manner in which this was achieved was shown in a slide of the Frémont apparatus. After the specimen had been fractured by the blow from the knife, rigidly attached to the base of the tup, the latter struck the anvil plate and depressed it against the resistance of the supporting springs. The downward movement of the anvil plate was transmitted by a light tube, sliding without friction, to a crank lever with very unequal arms. The long arm was really a pointer moving in front of a calibrated scale, so that the remaining energy which had been spent in compressing the spring could be read off directly. It was found in his laboratories that an improvement on this method was to allow the tup to fall on a small copper cylinder or crusher-gauge placed on the anvil. This cylinder, the length of which had been carefully measured, was compressed to an extent proportional to the energy still remaining in the tup after the work of fracture had been accomplished, the compression being then duly measured and converted into kilogram-metres or foot-pounds by means of a suitable Table. This method had proved to be more sensitive and more accurate. Mr. Frémont stated that it was most important that the weight of the anvil in shock-testing apparatus employed to test the brittleness of steel should be very considerable—approximately forty times as much as that of the falling weight. He contended that, if this were not so, incorrect results were obtained. By the invention of shock-testing apparatus the engineering world had received a very valuable adjunct and assistance to ensure safe material to meet the very severe stress of modern conditions. In other words, these methods enabled the fragility of the steel or other product to be carefully measured, this fragility varying more or less with the correct composition, heat treatment and general quality of the specimens taken from the manufactured product. The original discovery

Sir Robert
Hadfield.

Sir Robert
Hadfield.

of accurately determining shock-test qualities, as devised by Mr. Frémont, also included the use of a pendulum or swing hammer—suggested by him to the *Académie des Sciences* on the 4th October, 1897. The method was further elaborated by him in two Papers presented to the *Société des Ingenieurs Civils de France*, the first, “*Études de Chaudronnerie*,” being published in the Society’s *Bulletin*, November, 1897. That Paper gave a complete and accurate description of shock-tests on specimens nicked on one face to a depth of 1 millimetre and a width of 1 millimetre, which was exactly the same pattern as was used to-day in the Frémont apparatus. In that Paper *Figs. 26, 27, 28 and 29* showed shock test-pieces before and after fracture, and a full description was given of the compressible spring arrangement which absorbed the remaining energy of the blow, to which he had referred. A second Paper to the same Society on “*New Apparatus Used for the Testing of Metals*” was presented in December, 1898. In this a Frémont drop-tup apparatus was shown, and full references were given to shock tests of various kinds. In a further communication to the International Testing Association at Paris in 1900, it was mentioned that the employment of a pendulum for breaking the specimens could, if desired, be made. Confirmation of his statement with regard to the merit of the work performed by Mr. Frémont was to be found in a recent valuable Paper by Mr. André Cornu-Thénard.¹ The vertical tup type of shock-testing apparatus was probably the oldest of all, and was used by Mr. André Le Chatelier for his first experiments. It was, of course, not suggested that no one had previously carried out shock tests on small bars with falling weights; this was more or less current practice, specially in France, but not upon nicked bars, nor were devices for measuring the remaining energy employed. The ordinary vertical tup type of shock-testing apparatus previously used aimed at subjecting specimens to repeated blows, starting from a fixed height, and the resistance of the material was defined as the number of impacts which the bar withstood before breaking. This method, however, would not properly detect brittle material. The *modus operandi* was modified in 1893 by Mr. Barba, who determined by successive experiments on a number of specimens the greatest height of fall which the test-piece would resist without fracture. This also would not sift out bad material. Moreover, the first procedure had the disadvantage of producing at successive

¹ “*Étude expérimentale sur les essais au choc des barreaux entaillés*,” *Revue de Métallurgie*, August–October 1920.

stages cold working of the material, for which it was difficult to make an allowance. The second necessitated the use of many test-pieces, and consequently considerable waste of material to obtain a single result. A test also entailed an appreciable loss of time. To obviate these disadvantages Mr. Frémont, in 1897, devised the method of expressing the remaining energy of the tup as a function of the compression of a spring, or crusher gauge, so that only one drop of the tup was necessary to determine the work of fracture on each specimen. He would have liked to show a Frémont machine at work, but it was too large for that to be practicable. A comparatively new and excellent shock-testing machine had, however, been devised by another French engineer, Mr. Guillery, one of which he exhibited, and which furnished similar information to that from the Frémont apparatus. The Guillery machine consisted of a totally-enclosed steel flywheel rotated by hand. The speed of rotation was indicated by the height of coloured liquid in a vertical glass tube, which was virtually a liquid tachymeter. When the rotation had reached the desired point, as indicated by the height of the liquid corresponding to a linear velocity of a point on the rim of the wheel of 29 feet per second, a sliding knife in the rim of the wheel was released by a catch, and the knife then struck and fractured the test-piece, which had been suitably fixed on a die at the side of the machine. The energy extracted from the rotating wheel was indicated by the fall of the liquid column, the tube being calibrated so that the energy absorbed in fracture could be read off. He specially referred to this apparatus, because of its convenience and utility. [Sir Robert Hadfield and Mr. Main here carried out several experiments showing the breaking of different steel specimens, both tough and brittle, with the portable Guillery machine.]

Messrs. Jones and Greaves, in their very interesting Paper, described "overstrain" as "strain beyond the elastic limit," and pointed out that, in addition to its marked influence on the elastic limit, yield-point, and hardness, this condition of the material might produce an appreciable effect on other mechanical tests. In his Paper on "Manganese Steel" in 1888, he considered this question of the qualities of overstrained steel, and presented particulars of certain tests on a bar of medium hard-carbon (0·40 per cent.) steel, which gave very interesting results. Although shock tests were not taken, it might be useful to refer to the results obtained on the tensile test-bar in question, especially in view of the references to overstrain by Messrs.

Sir Robert
Hadfield.

Jones and Greaves. The bar was tested on an effective length of 2 inches by 0.797 inch in diameter, and the material in its normalized condition showed

Yield-Point.	Breaking Load.	Elongation on 2 Inches.	Reduction in Area.
Tons.	Tons.	Per Cent.	Per Cent.
27	38	27	34

Another bar of the same steel was strained eleven times—about 7 per cent. or 8 per cent. at each operation ; and between each test it was heat-treated—that was, normalized in the ordinary manner. On the eleventh test, when the bar finally broke, the following figures were obtained :—

Yield-Point.	Breaking Load.	Elongation.	Reduction in Area.
Tons.	Tons.	Per Cent.	Per Cent.
33	49	8½	83

From the eleven separate tests the total elongation was 113 per cent.—that was, the bar had been elongated to 4.27 inches. This bar and the Table of tests were shown in one of the lantern slides he exhibited. He had had prepared an interesting Table which illustrated in one compact statement the relation between Brinell ball and scleroscope hardness numbers, also tenacity, yield-point, compression strength, Frémont and Izod shock qualities of various types of steel, including ordinary carbon and alloy steels. Accompanying it was the conversion Table of the work required to fracture nicked Frémont and Izod specimens in foot-pounds. Also hardness of microconstituents of steel with Fe as unity. He proposed to add this Table to the Paper.¹ In conclusion he expressed his thanks for the able assistance rendered by his collaborator in the Paper, Mr. Main.

Dr. Unwin. Dr. W. C. UNWIN, Past-President, remarked that there were so many apparently anomalous results in notched-bar testing, and such diversity of opinion, that a very frank discussion, he thought, was wanted. He would pass over for the moment any criticism of the three Papers. Some things he would say would differ from the things which Sir Robert Hadfield had put forward, but he believed the real difference between them was that Sir Robert dealt chiefly with what Dr. Unwin called abnormal material and with velocities which were not the velocities ordinarily used in shock testing, while Dr. Unwin

¹ See Table X (pp. 162-163).

was dealing with the ordinary notched-bar test as it was commonly used. He thought the thing that had been really learned in the last 4 or 5 years was that notched-bar tests discriminated between what he, for convenience, called normal and what, for convenience, he called abnormal material. Normal material behaved in a perfectly consistent way in the notched-bar test, while abnormal material gave a low notched-bar test and behaved more or less erratically. Normal material was what an engineer would always use if he could get it, and he would not use abnormal material unless he was obliged to do so. He believed that Messrs. Frémont and Charpy, who introduced the notched-bar test in Europe, looked on the test as an empirical one, which in some way indicated a quality in materials to which they gave the name of fragility, and which was not shown in any ordinary testing used at that time. As far as he knew, every test which was carried to the point of fracture was an empirical test; there was no rational account of any test when the test was carried to fracture. To take one case, there was an exceedingly valuable test, known as the cold-bend test, which was purely empirical, and he remembered discussing some discordant test sheets with Sir Benjamin Baker, when Sir Benjamin remarked: "Well, you know, when there is a doubt I always look to the cold-bend test," and he thought Sir Benjamin Baker was right. Mr. Cornu-Thénard gave¹ a series of tests of similar notched bars, half of which were broken with a striking velocity of $17\frac{1}{2}$ feet per second and the other half were broken by slow bending at a velocity of $2\frac{1}{2}$ inches in 1 hour. Probably that was about as extreme a case as could be taken. Mr. Thénard found that within generally about 10 per cent.—or at most 20 per cent.—he got the same results from the impact tests and the slow bending test. That, he thought, was true of all material which came within the description of what he called normal material; it showed that for normal material the notch was essential, but it was not essential whether the material was broken by a blow or by slow bending. Mr. Thénard found at once an exception to that. The first really abnormal material which came to the notice of the British Engineering Standards Committee was some embrittled steel which Sir Robert Hadfield was kind enough to send, and Dr. Stanton at once found that the brittle steel, unlike normal steel, was very sensitive to the effect of speed or striking velocity. To give another illustration, Mr. Thénard tried some extra-soft mild steel in its normal state, and then rendered it coarsely crystalline by

¹ *Comptes Rendus*, vol. clxviii (1919), p. 1315.

Dr. Unwin. heat treatment in his laboratory. The normal mild steel broke under the slow bending test at 6.98 kilogram-metres, and under the impact test at 8.54. In that case the increase was 18 per cent. Taking the coarsely crystalline steel, it broke with the slow bending test at 3.71, but with the impact test it broke at 1.06, a difference of about 250 per cent. That showed very strikingly the difference of what he was classing as normal material and as abnormal material. Dr. Stanton had referred to a Paper by Mr. Charpy read before the Iron and Steel Institute.¹ It was really a Paper by Messrs. Charpy and Thénard and should be considered in relation to the Paper which appeared some time earlier in the *Comptes Rendus*² covering the same ground. Dr. Stanton said that they took extraordinary trouble and obtained extraordinarily consistent results. They did one thing which was generally neglected: they carefully normalized their test-bars before they broke them. They were testing a method, not a material, and they normalized the bars. Under those conditions they did get very consistent results. They got nearly the same results with four or five different testing-machines, and they found—what he did not think had been disturbed by later investigations—that with normal material of that kind, with striking-velocities ranging from 9 feet to 36 feet per second, there was no appreciable speed effect. Of course it would be different with abnormal material. About a year ago he showed in an article in *Engineering*³ that those very careful experiments of Messrs. Charpy and Thénard agreed very closely indeed with a simple formula. Let W be the work of fracture and a the section of bar, then $W = Ca^n$, C and n being constants for a given material. Since C was independent of the size of bar it might be taken as the notch-bar quality factor of the material. The following were values of n :—

	CHARPY AND THÉNARD.		
	Mild Steel.	Semi-hard.	Hard.
	1.18	1.25	1.34
			Copper.
			1.41
	STANTON AND BATSON.		
	Carbon	Carbon	Iron.
	0.19	0.45	..
V-notch	1.16	1.45	1.00
Charpy notch	1.26	1.40	1.05

For iron and mild steel the work of fracture varied approximately as the section, for hard steel and copper more nearly as the volume of

¹ Journal, Iron and Steel Institute, vol. xcvi (1917), p. 61.

² Vol. clxiv (1917), p. 473.

³ Vol. eviii (1919), p. 329.

the bar. From those two totally different series of experiments the value of the index n came out very much the same ; it varied for different materials, and varied in the same direction in each of the two series of tests. When the British Engineering Standards Committee met, it was faced primarily with the problem of finding a dimensional law. The Committee wanted to be able, from tests made with one size of test-bar, to predict the results on another size of test-bar. The Papers that had been read, he thought, were rather a confession that the Committee had failed in finding a dimensional law ; but if the formula he had put on the blackboard was accepted—a purely empirical formula, but one which had the sanction of agreeing with a good many experiments—the dimensional law was a very simple one. Denoting by W_a , W_b , the work of fracture of two similar and similarly notched bars, and x the ratio of their homologous dimensions, then $W_a/W_b = x^{2n}$. Taking Charpy and Thénard's results for 30-millimetre and 10-millimetre bars :—

	$\frac{W_{30}}{W_{10}}$	x^{2n}	x^2	x^3
Mild Steel	13·2	13·3	9	27
Semi-hard steel	12·4	12·5		
Hard Steel	18·9	19·0		
Copper	22·0	22·0		

For bars 30 and 10 millimetres, $x = 3$. Hence, if the work of fracture varied as the section of the bar or x^2 , the ratios should have been 9 ; if as the volume of the bar or x^3 , the ratios should have been 27. Obviously in these very consistent tests it was not so. The numbers were not all the same ; they were not 27, indeed, they were farther from 27 than from 9. It was an empirical result, but striking. Was there any possible way of accounting for the fact that the different materials had a different law in their resistance in different sizes ? He thought Mr. Main knew quite as well as he did himself that experiment did not support the rule that the resistance was proportional to the volume, but in Sir Robert Hadfield's and Mr. Main's Paper there was an argument that somehow or other it ought to. That seemed to him like saying : " This is my theory : if the facts do not agree with it, so much the worse for the facts." He thought it was possible to evade Mr. Main's argument, which was a hypothesis. He himself would give another

Dr. Unwin.

Dr. Unwin. hypothesis. It seemed to him that the energy expended in the fracture of a notched bar consisted of two entirely separate parts : there was some bending of the bar as a whole and the work expended in bending the bar as a whole might be proportional to the volume of the bar ; but then another part of the work of fracture was the work of the progressive extension of a crack at the notch, and that, he, suspected, must follow a wholly different law, which was not known at present. In fact, that was almost certain. The total energy of fracture, consisting of those two parts following two different laws, gave a relation for different sizes which was neither the square nor the cube and which for different materials might be different, because in different materials there was a different amount of bending before the crack began, and therefore the ratio of the two parts of the total energy was different in different materials. The abnormally low resistance of abnormal material seemed to be due to the fact that the cracking began with a very small amount of bending, and in that case the total amount of energy expended was very small. If the formula above was valid, C should be constant for a given material. A reduction of Dr. Stanton's results showed that it was nearly so, though as his bars were not normalized, the results were less consistent than Mr. Charpy's. The mean variation from the mean, or mean error, was generally less than that for each set of tests in Dr. Stanton's Table :—

VALUES OF n AND $C = \frac{W}{a^n}$ FOR DR. STANTON'S TABLE II.

Material . . .	OS.	OS. ¹	PE.	PE.	RL.	RL.
$n =$. . .	1·16	1·26	1·45	1·39	1·0	1·05
Notch . . .	V-	Charpy	V-	Charpy	V-	Charpy
Size.	Values of C .					
63 × 63 mm. .	5·38	5·66	1·65	1·36	3·62	2·64
30 × 30 „ .	6·08	3·86	2·08	1·59	3·97	4·15
15 × 15 „ .	6·4	3·44	2·04	1·28	2·69	2·06
10 × 10 „ .	6·18	3·42	1·41	1·37	4·08	2·8
Mean . . .	6·01	4·09	1·8	1·4	3·59	2·91
Mean error .	±0·31	±0·78	±0·27	±0·1	±0·45	±0·62
Mean error per cent. . .	5·2	18·9	15·0	7·0	12·5	21·0

¹ This series is anomalous.

Abnormal material was extremely sensitive to the striking Dr. Unwin. velocity with which it was broken, and therefore to discriminate it the testing-machine should give a sufficiently high velocity; it need not be a very high one, but must be sufficiently high. But it was not only that it behaved erratically with regard to the speed at which it was broken. Mr. Cornu-Thénard made some experiments with a very soft steel and with the same steel rendered coarsely crystalline, with different radii at the bottom of the notch. He used two notches, of 0·7 millimetre and 2 millimetres radius respectively. With the normal soft steel and 0·7-mm. radius the bar broke with 17 kilogram-metres and with the 2-mm. radius with 18 kg.-m. It was known that, the larger the radius of the notch, the larger the amount of energy required to break the bar. The coarsely crystalline steel with the larger radius of notch behaved quite differently from what it did with the smaller radius: with 0·7-mm. radius, the steel only took 1·7 kg.-m., but with the larger radius it took 12 kg.-m. That was one of the peculiarities of what he was calling abnormal steel. Mr. Thénard went further. By breaking bars without any notch at all, he found that the one steel was just about as good as the other. On p. 78, Dr. Stanton laid down the principle that, whatever the form of test-piece adopted for a series of tests of any two materials, with specimens geometrically similar but of different sizes, the *ratio* of the impact resistance must always be approximately the same, and he proceeded from that to deduce for two of his experiments, taking the two materials OS and PE, one soft and the other hard, that with the 63×63 millimetre test-bar the mild steel was 50 per cent. better than the hard steel, but that with the 10×10 millimetre bar it was 230 per cent. better. That was a very remarkable result. He thought Dr. Stanton had impaled himself on the horns of a dilemma. If his principle was right, and rightly stated, then those results proved that the notched-bar test was too erratic to be of any use and ought to be discarded. On the other hand, belief in the notched test involved the conclusion that there must be something wrong with Dr. Stanton's principle or with his statement of it.

Professor E. H. LAMB remarked that some apology was due from Professor Lamb. him for taking part in the discussion, as he had not been a worker in that particular branch of testing, but Dr. Stanton's Paper had set him thinking about the question of similarity and had driven him to an analysis of the dynamics of the tests, based on some simple assumptions, the results of which bore out some of the statements in Dr. Stanton's Paper about similarity, and incidentally might,

Professor
Lamb.

when written down, suggest an explanation of some of the so-called velocity effects, or at any rate a method of testing them. In dealing with the question of time-effects and velocity-effects in testing, he thought the whole range of time-effects had to be considered. At one end of it there was the statical testing-machine or something slower, and at the other end there was the fracture of ductile material, like a steel shell-case, by high explosives, where the initial part of the fracture apparently behaved exactly as in extremely brittle material. Between those two limits many things might happen; and up to the point where the crack started in the ordinary impact test some fairly reasonable assumptions could probably be made. After that there was some difficulty. [The speaker here gave a mathematical investigation on the blackboard, of which he has since communicated the note printed below¹.] Unfortunately the

¹ NOTE ON THE DYNAMICS OF IMPACT TESTS.

Let V denote the striking velocity of the hammer whose mass is M .

m	„	mass of specimen.
x	„	deflection of specimen.
k	„	reduced inertia coefficient.
P	„	resistance to motion of the hammer M and the inertia of the specimen km .

The hammer, on making contact with the specimen, has its velocity suddenly reduced from V to $\frac{M}{M+km} V$, and subsequently they move together against a variable resistance P provided by the molecular actions within the specimen. Hence the equation of motion is

$$(M + km) \ddot{x} + P = 0 \quad \dots \dots \dots (1)$$

As a reasonably approximate representation of P within the elastic range

$$P = ax + b\dot{x} \quad \dots \dots \dots (2)$$

and equation (1) is of the form—

$$\ddot{x} + 2\epsilon\dot{x} + n^2x = 0 \quad \dots \dots \dots (3)$$

Sir William
Ellis.

to recommend the adoption of the tests. Fortunately there were in various engineering works research laboratories staffed by very efficient metallurgists, and he would urge that engineers who had problems before them, in which they thought impact tests would furnish additional security, should take the opportunity of consulting the metallurgists who were at the head of those laboratories, or Dr. Stanton, Dr. Rosenhain, and others at the National Physical Laboratory. The members did not often have an opportunity of listening to such an interesting and clear discussion of a scientific Paper from one of their colleagues who was elected into The Institution 53 years ago, and he thought they would all join in congratulating Dr. Unwin and thanking him for his most interesting contribution to the discussion.

The foregoing observations with reference to the stress and the rate of strain at the bottom of the notch within the elastic range hold equally in this case, as well as the inference that geometrical similarity should not be extended to the radius at the bottom of the notch.

The result in (18) above appears to confirm the course adopted by Dr. Stanton and Mr. Batson, which is explained on p. 76, namely, the system of plotting the energy absorbed per unit volume of the specimen. Unfortunately, however, the quantity of energy absorbed, as measured on the testing-machine, is not U_0^t up to the time when fracture commences; but includes all the subsequent energy absorbed in tearing and shearing the material after the initial crack has started the process, as well as a considerable amount of external friction work spent in forcing the specimen in between the stops, and the kinetic energy of the fractured specimen.

There remains still the obscure point as to what combination of circumstances ultimately determines the initial fracture. The initial crack at the bottom of the notch takes place when the cohesive strength of the material at this point has deteriorated (owing to the shearing, etc.) to the value P as estimated in (17) above. For geometrically similar specimens this deterioration might reasonably be the same if the radius at the bottom of the notch is the same for all sizes, except for the fact that the stress distribution across the specimen at this point is not the same. The effects of this may of course be considerable, and may be sufficient to account largely for the fact that the energy absorbed per unit volume as measured is not constant.

The theory sketched above also suggests some possible experiments to determine the effects of stress distribution and rate of straining in specimens of geometrically similar form on the deterioration of the molecular cohesive strength at the bottom of the notch. It seems probable also that some estimate of the velocity coefficients in the assumed expressions for P could be made by rebounding tests with the hammer at low velocities.—E. H. L.

Dr. STANTON and Mr. BATSON, in replying to the discussion, Dr. Stanton and Mr. Batson. expressed their gratification that Dr. Hatfield should find so much in their Paper with which he was in agreement. They felt, however, that they ought to say emphatically that they could not follow him in his rejection of the test. With the restrictions mentioned in the Paper they were strongly of opinion that the test was a most valuable one, affording as it did a means, and apparently the only mechanical means, of determining whether a material was in its best condition to resist shock stresses. If Dr. Hatfield's arguments against the test were examined they would be found to be based mainly on the good behaviour in practice of materials having an admittedly low impact figure. For example, he cited the case of certain crank-shafts of long and meritorious service which, on the results of impact tests on specimens cut from them, would have been rejected by the Aeronautical Inspection Directorate. From this evidence Dr. Hatfield, as a metallurgist, drew the not unnatural conclusion that the test was worthless. The Authors, however, as engineers, would prefer to say that the shafts were satisfactory for the not very recondite reason that they had no notches in them, or, in other words, that they were designed by a man who was thoroughly conversant with the behaviour of materials in practice. Unfortunately, the number of such men was limited, and for this reason the Authors held that the Aeronautical Inspection Directorate was perfectly justified in fixing a moderately high impact figure for their acceptance tests, for in doing this they were ensuring to the best of their ability that the material used for such crank-shafts was what might be called "design fool-proof." In reply to Mr. Green's questions, the notches were made after heat treatment. Had they been made before heat treatment the danger of a crack developing at the bottom of the notch would have been considerable. The method of obtaining different velocities of striking was not indicated in Fig. 2, Plate 1. The machine was fitted with an extension of the frame consisting of a pair of angle-bars in the form of a circular arc, occupying the position shown by the dotted circle in Fig. 2, and by bolting the release attachment to any point in the arc, intermediate values of the speed could be obtained. As regarded the cylindrical specimens notched all the way round, the Authors had had no experience with specimens of this type, but they understood that the Aeronautical Inspection Directorate considered them nearly as satisfactory as the square type and very much cheaper to make. Experience at the National Physical Laboratory had shown that by the use of the special jigs, made for the purpose, the standard square specimen could be machined and notched in the

Dr. Stanton and Mr. Butson. lathe by milling cutters at less cost than the cylindrical specimens. For the tests described in their Paper, owing to the fact that it was found to be much easier to notch the 30×30 and 63×63 millimetre specimens by means of a shaping tool than by a milling cutter, it was decided, in order to obtain uniformity, to notch the test-pieces of all sizes by means of a shaping tool. They could not agree with Mr. Humfrey's conclusions that the form of the energy-dimension curve for similar notched specimens was parabolic, as it was always easy to find a parabola which would fit a portion of any curve, but it could not be assumed that it would fit the whole of it. In their opinion, the work of fracture per unit volume of the specimen approached a limiting value as the linear dimensions increased. With reference to Mr. Saniter's remarks as to the effect of the width of the specimen being to reduce the dimensional effect, and his suggestion to use a specimen which was notched on three sides, they hoped to adopt this suggestion in future work on the subject, and considered it highly probable that Mr. Saniter's expectations would be realized. Dr. Unwin's criticisms of the statements on p. 78 appeared to the Authors to be based on a misunderstanding which it was most desirable to clear up. The statement in the Paper to which Dr. Unwin took exception was that in the notched-bar tests of two of the materials used for the research, one a mild steel and the other a hard steel, when the specimens were 63×63 millimetres, the ratio of the impact resistance of the mild steel to that of the hard steel was 1.50, and that when the specimens were exactly similar but 10×10 millimetres, the ratio was 3.70. Now this statement was not, as might be inferred from Dr. Unwin's remarks, deduced from some general law of impact resistance, but was the result of direct observation of the energy absorbed in fracture. The only possible criticism of the statement which could be made was that owing to personal errors or inaccuracies in the testing-appliances those figures did not represent the facts. They were convinced, however, from check tests and from recalibration of the testing-machines, that the figures did represent the facts. They agreed that if the observed facts could be accurately represented by the relation suggested by Dr. Unwin, namely—energy of fracture = ka^2 , where a was the square of the linear dimension and k was a constant, the same ratios as those given above should be obtained by calculation, and for this reason they had carefully re-examined the experimental results with a view to find whether satisfactory evidence of such a law existed. In the case of the hard steel no such relation had

been found to exist, and this afforded a complete explanation of the discrepancy to which Dr. Unwin had called attention. The facts stated did not place them in any dilemma, but fully confirmed their views as to the danger of disregarding the effects of size in notched-bar testing.

Messrs. GREAVES and MOORE, in reply, remarked that several facts had emerged in the Papers and discussion which supported their view that localization of stress was the most essential feature of the notched-bar impact test. Professor Lamb had indicated that on theoretical grounds geometrical similarity of test-pieces should not be extended to include geometrical similarity of the radii of the notches. If it were so extended, the larger the test-piece, the more rounded would be the notch and the less the concentration of stress. This probably explained why, in the large test-pieces of Dr. Stanton and Mr. Batson, the difference between the tough and brittle steels was relatively much less than in smaller test-pieces. The more rounded notch of the large test-piece made the test less discriminating; as the size of the test-piece was increased, the test lost its characteristic feature of concentration of stress. They had had experience in the use of Mr. Humfrey's slow-bending machine, and considered that its autographic diagrams threw much light on the mechanism of deformation and breaking in the notched-bar test. They were in entire agreement with Mr. Humfrey in his analysis of the factors contributing to the energy measured in the impact test, and in regarding the latter part of the curve of his autographic diagram as indicating the capacity of the material to resist the propagation of a crack. With regard to the important practical question of the utility of the notched-bar impact test, they were sorry to find themselves in disagreement with Dr. Hatfield; but a further examination of their respective statements led to the view that the disagreement might not be so fundamental as it at first appeared. Dr. Hatfield had stated that "no instance had occurred within his experience in which the failure of a part in service had been explained by low values under the notched-bar test." Taking the view set forth in the Paper that the notched-bar test was most usefully regarded as a test of deformability under localized stress, the impact figure had no bearing on serviceability so long as the elastic limit was not exceeded at any point of the material. The same statement applied to elongation in the tensile test. The sole reason for demanding a capacity for plastic deformation in engineering materials was the risk of the elastic limit being exceeded locally

Dr. Stanton
and
Mr. Batson.

Messrs.
Greaves and
Moore.

Messrs.
Greaves and
Moore.

by the application of high localized stress. They would be the last to say that it would be wrong to ascribe a failure to some cause (such as the presence of defects, flaws, or inclusions, errors of design, etc.) which was ultimately responsible for producing local stresses in excess of the elastic limit; but it was easy in such cases to overlook the effect of poor resistance to the formation or propagation of a crack. They might take the case of temper brittleness of nickel-chromium steel, in the detection of which the notched-bar test probably had at present its most important application. It was their experience of the behaviour of temper brittle nickel-chromium steel in service that had convinced them of the necessity of demanding a minimum impact figure. They might give some further indication of the nature of the evidence. They had examined a number of nickel-chromium steel forgings—some very large, some of medium size—which had failed by sudden fracture. Of all those examined within a period of about 3 years, whatever the ultimate cause of the failure, 80 per cent. were found to be in the temper brittle condition, giving Izod impact figures of from 3 to 9 foot-lbs. The proportion of temper brittle forgings in service at the same time was comparatively small. They had in addition kept under observation forgings which contained “hair-line” cracks. In three such forgings with impact figures of over 20 foot-lbs. (transverse tests) the hair-line cracks had extended so gradually as not to interfere with the normal life of the material. Similar forgings in the temper brittle condition, stressed in precisely the same way, had failed suddenly by cracking. They did not wish to imply that all forgings showing marked temper brittleness would behave in this way, seeing that a condition of dangerously high localized stress might never arise; but at the least it might be claimed that the demand for a reasonably good impact figure would tend to eliminate the class of steel in which failures were most liable to occur.