Cite this article

Black L and Tyrer M (2018)
Editorial: Selected papers from the 36th Cement and Concrete Science Conference, Cardiff University, September 2016.
Advances in Cement Research **30(8)**: 323–324,
<https://doi.org/10.1680/jadcr.2018.30.8.323>

Editorial

ICE Publishing: All rights reserved

Editorial: Selected papers from the 36th Cement and Concrete Science Conference, Cardiff University, September 2016

Leon Black

Professor of Infrastructure Materials, School of Civil Engineering,
University of Leeds, Leeds, UK

Mark Tyrer

Professor of Geomaterials, Coventry University, Coventry, UK

This Special Issue of *Advances in Cement Research* presents a selection of the papers presented at the 36th Cement and Concrete Science Conference, held on the 5–6th September 2016, at Cardiff University. The meeting was organised by Gary Perkins of The University of South Wales and Mark Tyrer of Coventry University on behalf of the Cementitious Materials Group of the Institute of Materials, Minerals and Mining (IOM³).

The annual conference brought together a mix of academic and industrial partners with a number of papers presented over the two days, and while having a UK focus, the conference has grown over the years into a truly international event. As every year, the 2016 conference was a friendly affair, with a wide range of topics covered. This breadth is reflected in the contributions to this Special Issue, with papers on applications in the nuclear industry, concrete durability and recycled geopolymers all featuring.

There are three papers related to nuclear aspects, all from the group at the University of Sheffield. Collier *et al.* (2018) followed up their earlier work into retardation of deep bore-hole disposal grouts by looking at the retarding effects of sodium phosphate and borate, tin chloride and zinc nitrate at high temperature and pressure. Only sodium borate was found to be an appropriate retarder, with 0.75 wt% addition at 90°C.

The papers by Sanderson *et al.* (2018) and Prentice *et al.* (2018) both considered the performance of cement-GGBS blends as used for intermediate level nuclear waste encapsulation. Sanderson *et al.* built on their earlier use of calorimetry to examine cement-GGBS blends (Sanderson *et al.*, 2017) and examined the hydration of cement-slag blends, considering the effect of calumite, a coarse-ground slag used in nuclear waste encapsulation to modify rheology, on hydration and rheology. Prentice *et al.* (2018) meanwhile used thermodynamic modelling supported by NMR and XRD applied to cement-GGBS blends. While ²⁹Si NMR was found to accurately follow the degree of hydration, there is still room to improve the

structural characteristics of the C-A-S-H gel using thermodynamic modelling.

Meanwhile, Chaliasou *et al.* (2018) examined a topic of potentially growing importance, namely what to do with geopolymers at the end of their service life. While there has been work looking at the use of geopolymer concrete made with recycled concrete aggregate (such as Nuaklong *et al.*, 2016) and the use of recycled concrete in Portland cement concrete – for example Collery *et al.*, 2015, there does not appear to have been any previous work examining how recycled geopolymers may affect concrete durability within a Portland cement matrix. Their work suggests that concerns over alkali silica reaction, when recycling geopolymers, are unfounded.

The remaining two papers concern more traditional applications of Portland cement, both being focused on the durability of composite cements. Ukpata *et al.* (2018) examined the effects of temperature, slag composition and curing duration on the performance of cement-GGBS blends exposed to a combined sodium sulphate sodium chloride solution. The work builds on work on the same systems exposed to just chloride ions (Ogirigbo and Black, 2016; Ogirigbo and Black, 2018). Using a range of analytical techniques, they have shown that slag cement outperforms CEM I in tropical environments and that the effects of sulphate attack are mitigated by the presence of chlorides.

Freeze-thaw resistance is the topic of the final paper. Using a combination of phase characterisation and microstructural investigation, Adu-Amankwah *et al.* (2018) have looked at the freeze-thaw resistance of ternary cement-slag-limestone mixes. It is known that composite cements can show reduced resistance to freeze-thaw testing, and having previously characterised the microstructures and phase assemblages of such systems (Adu-Amankwah *et al.*, 2017), this paper goes on to show how the poor performance under laboratory-based freeze-thaw testing may be related to leaching of portlandite. This goes some way to explaining why composite cements may perform poorly in standardised freeze-thaw tests.

Finally, it remains for us to say thank you to everyone involved in producing this Special Issue. Thanks go to the authors, many of whom were PhD students during the conference, the anonymous referees for their valuable comments, and to the staff at Thomas Telford and ICE Publishing. We hope that you enjoy reading this Special Issue as much as we enjoyed collating it.

REFERENCES

- Adu-Amankwah S, Zajac M, Stabler C, Ben Haha M and Black L (2018) Relationship between cement composition and the freeze–thaw resistance of concretes. *Advances in Cement Research* **30(8)**: 387–397, <https://doi.org/10.1680/jadcr.17.00138>.
- Adu-Amankwah S, Zajac M, Stabler C, Lothenbach B and Black L (2017) Influence of limestone on the hydration of ternary slag cements. *Cement and Concrete Research* **100(1)**: 96–109, <https://doi.org/10.1016/j.cemconres.2017.05.013>.
- Chaliasou NA, Heath A, Paine K and Calabria Holley J (2018) Chemical aspects related to using recycled geopolymers as aggregates. *Advances in Cement Research* **30(8)**: 361–370, <https://doi.org/10.1680/jadcr.17.00120>.
- Collery DJ, Paine KA and Dhir RK (2015) Establishing rational use of recycled aggregates in concrete: a performance-related approach. *Magazine of Concrete Research* **67(11)**: 559–574, <https://doi.org/10.1680/mac.14.00206>.
- Collier NC, Balboa HE, Milestone NB and Travis KP (2017) Inorganic anions as retarders for deep borehole disposal grouts. *Advances in Cement Research* **29(8)**: 347–357, <https://doi.org/10.1680/jadcr.17.00183>.
- Collier NC, Pawar SH, Milestone NB and Travis KP (2018) Deep borehole disposal grouts – are inorganic retarders appropriate? *Advances in Cement Research* **30(8)**: 387–397, <https://doi.org/10.1680/jadcr.17.00116>.
- Nuaklong P, Sata V and Chindaprasit P (2016) Influence of recycled aggregate on fly ash geopolymer concrete properties. *Journal of Cleaner Production* **112(4)**: 2300–2307, <https://doi.org/10.1016/j.jclepro.2015.10.109>.
- Ogigirbo OR and Black L (2016) Influence of slag composition and temperature on the hydration and microstructure of slag blended cements. *Construction and Building Materials* **126**: 496–507, <https://doi.org/10.1016/j.conbuildmat.2016.09.057>.
- Ogigirbo OR and Black L (2018) The effect of slag composition and curing duration on the chloride ingress resistance of slag-blended cements. *Advances in Cement Research*, <https://doi.org/10.1680/jadcr.17.00152>.
- Prentice DP, Bernal SA, Bankhead M, Hayes M and Provis JL (2018) Phase evolution of slag-rich cementitious grouts for immobilisation of nuclear wastes Prentice. *Advances in Cement Research* **30(8)**: 345–360, <https://doi.org/10.1680/jadcr.17.00198>.
- Sanderson RA, Cann GM and Provis JL (2017) Comparison of calorimetric methods for the assessment of slag cement hydration. *Advances in Applied Ceramics* **116(4)**: 186–192, <https://doi.org/10.1080/17436753.2017.1288371>.
- Sanderson RA, Cann GM and Provis JL (2018) The effect of blast-furnace slag particle size on the hydration of slag–Portland cement grouts at elevated temperatures. *Advances in Cement Research* **30(8)**: 337–344, <https://doi.org/10.1680/jadcr.17.00136>.
- Ukpata JO, Basheer PAM and Black L (2018) Performance of plain and slag-blended cements and mortars exposed to combined chloride–sulfate solution. *Advances in Cement Research* **30(8)**: 371–386, <https://doi.org/10.1680/jadcr.17.00121>.