Further discussion on an article published in the

Magazine of Concrete Research

Volume 8, Number 22 : March 1956

Maturity and the strength of concrete*

by J. M. Plowman, B.Sc.(Eng.), Ph.D., A.C.G.I., D.I.C., A.M.I.C.E.I.

Contribution by D. H. Tyler, B.E.
(University of Adelaide)

Plowman uses the relation:
percentage of strength at maturity of 35,600°F hr = $A + B \log_{10} \left(\frac{\text{maturity}}{10^3} \right)$

In this relation the constant *B* represents a unique property of any concrete for which the compressive strength at a given maturity is known. Graphically, if the percentage of strength at a maturity of 35,600°F hr is plotted against log₁₀ (maturity), through a point having the co-ordinates 100% of strength at 35,600°F hr and 35,600°F hr maturity. The constant *A* is seen to depend solely on the value of *B* (Figure I).

“Exact values” of *B* for different strengths at a maturity of 35,600°F hr are given in Table 3 of Plowman’s paper. Strengths at maturities other than 35,600°F hr may be derived as indicated in the Appendix.

For example,
Strength at maturity of 3,560°F hr = (100—*B*)% of strength at maturity of 35,600°F hr.

Tabulating we have:

Strength at a maturity of 35,600°F hr	<i>B</i> (from Table 3)	Strength at a maturity of 3,560°F hr
9,000	46	4,860
8,000	49	4,080
7,000	52	3,360
6,000	55	2,700
5,000	58	2,100
4,000	61	1,560
3,000	64	1,080
2,000	67	660
1,000	70	300

This Table provides sufficient data for drawing Figure II. It may be used, for example, in the following way.

If the strength of a given concrete is known to be 2,500 lb/in² at a maturity of 7,000 F hr, then point 1 on the graph may be located and the line *ab* interpolated. Hence the strength for any other maturity of this concrete may be found; for example, point 2 shows that at a maturity of 40,000 F hr the strength of this concrete would be 4,400 lb/in².

*Pages 13-22.

Figure I

Figure II