Discussion on paper published in

Magazine of Concrete Research

1995, 47, No. 172, Sept., 227–233

Web reinforcement

S. H. Ahmad, F. Park and K. El-Dash

Contribution by S. B. Desai

UK Department of the Environment

It seems that the authors have used the BS 8110 rule incorrectly in estimating the shear resistance of beams of type B given in Table 2 on page 229. They have applied the factor $(2d/a)$ for beams with shear span in excess of 2, which is incorrect. With this correction, the BS 8110 value of v_c for beams B7H and B8H with f_c of 42.8 N/mm² will be 1.09 N/mm² and not 0.55 N/mm². Also, the BS 8110 estimate will be closer to the authors' ACI code estimate of 1.08 N/mm².

The authors also appear to exclude the effect of shear span ratio given in ACI Code Rule 11-30.

While the BS 8110 estimates seem to include a γ_m factor of 1.25, the authors exclude the strength reduction factor ϕ (0.85, ACI Code Section 9.3) for the ACI code estimates. The comparison between the codes, therefore, is not equitable.

I agree that the BS 8110 rule limit for enhancement of v_c with f_{cu} should be extended beyond an f_{cu} of 40 N/mm², say up to 60 N/mm². The other conclusions drawn by the authors are, however, clouded by the apparently inappropriate application of the rules given in the codes.

When applying the BS 8110 rule, the authors should have used the characteristic value of concrete

strength as the cube strength and not the cylinder strength (f'_c). With this amendment, the corrected BS 8110 values of V_c/bd (MPa) for beams of type B will be as in Table 1.

Reply by the authors

The authors appreciate the interest and the useful comments offered by Mr Desai. In the paper, the authors considered the shear span effect in BS 8110 outside its proper range and used the cylinder strength instead of the characteristic value of concrete strength as the cube strength. With this amendment, the BS 8110 values of V_c/bd (MPa) for beams of type B should be revised as suggested by Mr Desai.

The strength reduction factor of 1.0 was used for the ACI code estimates.

Table 1. Corrected BS 8110 values of V_c/bd for beams of type B: MPa

	B3H	B4H	B5H	B6H	B7H	B8H
Authors' values	1.24	1.26	0.90	0.88	0.55	0.55
Corrected values	1.33	1.35	1.01	0.99	1.09	1.09